

Multistrato Carply Fenolico Wiremesh in legno di Eucalipto

Technical Data Sheet

Product	Film/ Film and Wiremesh/Film Faced Plywood
Specification	2500x1250x30mm/24mm/21mm/18mm/15mm/12mm
Wood Species	Eucalyptus
Glue	WBP Phenol Glue to meet bonding EN314-2, Class 3; EN636-3.
Film	Smooth side: 120gr/m² Phenol Film; Wiremesh side: 240gr/m² Phenol film
Moisture Content	8-12%
Density	580kg/m³
Thickness Tolerance	0.5mm
Tolerance in Length and width	1.0mm
Bending Strength	long Grain: 35-45 N/mm²
	Cross: Grain: 45-55 N/mm²
Modulus of Elasticity In Bending	long Grain: > 6000 N/mm²
	Cross Grain: > 7000 N/mm²
Reaction to Fire Class	D- s2, d0.